

Viscosity Conversion Table

Centipoise	Gardner Holdt Bubble	Krebs- Stomer KU	Saybolt Universal SSU	Ford Cup 3	Ford Cup 4	Zahn Cup 1	Zahn Cup 2	Zahn Cup 3	Zahn Cup 4	Zahn Cup 5
10	A4		60		5	30	16			
15	A3		80		8	34	17			
25	A2		130	15	12	41	19			
30	A1		160	19	14	44	20			
40	A		210	25	18	52	22			
60	B	33	320	33	25	68	27			
80	C	37	430	41	31		34			
100	D	40	530	50	34		41	12	10	
120	E	43	580	58	41		49	14	11	
140	F	46	690	66	45		58	16	13	
160	G	48	790		50		66	18	14	
200	H	52	1,000		58		82	23	17	10
220	I	54	1,100		62			25	18	11
240	J	56	1,200		65			28	20	12
280	K	59	1,380		70			32	22	14
300	L	60	1,475		74			34	24	15
320	M		1,530					36	25	16
340	N		1,630					39	26	17
360	O	62	1,730					41	28	18
400	P	64	1,950					46	30	20
440	Q		2,160					50	33	22
460	R	66	2,270					52	34	23
500	S	68	2,480					57	37	25
550	T	69	2,660					63	40	27
600	U	71	2,900					68	44	30
900	V	81	4,300						64	45
1,000	W	85	4,600							49
1,300	X	95	6,100							64
1,700	Y	101	8,000							
2,300	Z	105	10,750							
2,500	Z1	114	11,600							
3,500	Z2	129	16,500							
4,500	Z3	136	21,000							
6,000	Z4		28,000							
10,000	Z5		46,500							
15,000	Z6		69,500							

All viscosities based on measurements taken at 25°C



Dianal America, Inc.
 9675 Bayport Blvd.
 Pasadena, TX 77507, USA
 Phone +1 713-758-8100
 Toll Free 800-776-3659
 Fax +1 281-474-2757
www.dianal.com

